

# BC240B

Enduraflex™ black, soft, neoprene lining for general purpose use.

## SPECIFICATIONS

**PRESSURE CURE:**

35 to 45 A

**AVAILABLE GAUGES:**

1/8", 3/16", 1/4", 3/8", 3mm, 4mm, 5mm, 6mm

**SKIVE:**

Open

**REPAIRS:**

Repair with original lining.  
See Section 16 – Repair Procedures.

## TYPICAL PHYSICAL PROPERTIES


Tensile Strength PSI	ASTM D412	1700
% Elongation at Break	ASTM D412	750
Durometer	ASTM D2240	40 A
Specific Gravity	ASTM D297	1.39
Adhesion to Metal	ASTM D429	25 LBS

Notes: For the best appearance of the completed rubber lining, always apply plastic side down against the substrate.

## CURE METHODS AND TIMES:

Autoclave	1 hour at 275°F (135°C)
Molded Temperature	20 minutes at 260°F (127°C)

Note: Cure times may require adjustment to compensate for heavy metal thickness, low exterior temperatures or other unusual factors. See Section 14 – Curing Instructions.



## BC240B Enduraflex™ black, soft, neoprene lining for general purpose use.

### STORAGE LIFE FROM DATE OF SHIPMENT

32°F (0°C) to 50°F (10°C)	180 days
51°F (13°C) to 65°F (19°C)	90 days
66°F (21°C) to 75°F (23°C)	60 days
76°F (23°C) to 85°F (30°C)	30 days

Storage temperature must not exceed 85°F (30°C)

### ADHESIVE SYSTEM ENDURABOND™ 1\*2\*3 SYSTEM

1st coat on metal:	Primer P-100
2nd coat on metal:	Intermediate I-100
3rd coat on metal:	201 Tack
On the rubber:	201 Tack

\*Each adhesive component requires thorough mixing before application.

### APPLICATOR NOTES

1. Ideal for molding applications.
2. Lining may shrink 10% length wise after unrolling. Preshrink rubber before applying.
3. The temperature of the substrate must be greater than 60°F (15°C) prior to applying primer and rubber. Temperatures should not exceed 120°F (49°C).
4. Strict adherence to adhesive specifications is required. Tack time is critical to the success of the bond.



### DISCLAIMER:

The above guidelines are based on general industry practices and not applicable to all installations. Please contact Blair Rubber Company for specific application instructions. Application methods shall conform to Blair Rubber Company instructions contained in the Engineering & Applicator manual. Deviations from the specifications must be approved in writing by Blair Rubber Company. Data values are approximate and may vary based on installation techniques and atmospheric conditions. As such, data values should be used as general guidelines and are not a legally binding warranty of product characteristics. This document is copyright to and the intellectual property of Blair Rubber Company and may not be copied or distributed without prior consent.